

HabasitLINK® Straight 1" Pitch Belting

M2520 Flat Top 1"





Description

- 0% open area
- High lateral stiffness
- Food approved materials available
- Rod diameter 5 mm (0.2")
- "Open window" sprockets

Available accessories

- Flights and Scoops
- Sideguards
- Hold down devices
- GripTop modules



Belt data

Belt material		PP		PE	POM	
Rod material		PP	POM	PE	PP	PA
Nominal tensile strength F'_N straight run	N/m	18000	18000	9000	21500	32000
	lb/ft	1233	1233	616	1473	2192
Temperature range	°C	5 - 105	5 - 93	-70 - 65	5 - 93	-40 - 93
	°F	40 - 220	40 - 200	-94 - 150	40 - 200	-40 - 200
Belt weight m_B	kg/m²	5.5	5.5	5.8	8.4	8.4
	lb/sqft	1.13	1.13	1.19	1.71	1.71

Diameter of idling rollers (minimum)		Diameter of support rollers (minimum)		Diameter for gravity take-up and center drive rollers (minimum)		Backbending radius for elevators without side- guards or hold down devices (minimum)		Backbending radius for elevators with sideguards or hold down devices (minimum)	
mm	inch	mm	inch	mm	inch	mm	inch	mm	inch
40	1.6	50	2	100	4	150	6	250	10

Use the largest possible backbending radius for elevators with side guards or hold down devices.

Standard range of belt widths b_0

mm (nom.)	50	100	150	200	250	300	350	400	450	500	550	600	650	700	etc.
inch (nom.)	2	4	6	8	10	12	14	16	18	20	22	24	26	28	etc.

Real belt widths are in most cases 0.1% to 0.3% wider.

Standard belt widths in increments of 50 mm (2"). Non-standard widths are offered in increments of 16.66 mm (0.66"). Smallest possible width 83.4 mm (3.25"). Non-bricklaid belts 50 mm (2") and 100 mm (4") wide.

For detailed material properties refer to the HabasitLINK® Engineering Guidelines or contact your Habasit representative.

The nominal tensile strength is valid for 23 °C (73 °F). The admissible tensile force depends on the operating temperature near the drive sprockets. Within the temperature range allowed, the admissible tensile force may vary from 100% to 20% of the nominal tensile strength. For detailed information and correct calculation of effective tensile force refer to the Calculation Guide in the HabasitLINK® Engineering Guidelines.

HabasitLINK® Straight 1" Pitch Belting M2520 Flat Top 1"



Belt data for special belt materials

Belt material		PBT +FR		PA +GF	ST	PA +HT
Rod material		PP	PA	ST		
Sprocket material ⁽¹⁾		Standard		ST		
Belt width		Standard		see table		
Flammability classification UL 94 ⁽²⁾		V0		HB	V0	HB
Flammability classification ISO 340 ⁽²⁾		yes		no	no	
Nominal tensile strength F' _N	N/m lb/ft	16000 1027	15000 959	24000 1644	12000 822	24000 1644
Temperature range	°C °F	5 - 105 40 - 220	-40 - 130 -40 - 266	0 - 145 32 - 293	0 - 200 32 - 392	0 - 170 32 - 338
Temperature maximum (short-term)	°C °F		150 302	175 347	240 464	200 392
Belt weight m _B	kg/m ² lb/sqft	8.9 1.82	8.9 1.82	9.0 1.85	10.8 2.21	9.0 1.85

Belt width for Polyamide +GF, Polyamide +HT and Super High Temperature material (ST)

mm (nom.)	50.8	101.7	152.5	203.3	254.2	305.0	355.8	406.7	457.5	508.3	559.2	610.0	etc.
inch (nom.)	2.00	4.00	6.00	8.00	10.01	12.01	14.01	16.01	18.01	20.01	22.02	24.02	etc.

Product liability, application considerations

If the proper selection and application of Habasit products are not recommended by an authorized Habasit sales specialist, the selection and application of Habasit products, including the related area of product safety, are the responsibility of the customer.

All indications / information are recommendations and believed to be reliable, but no representations, guarantees, or warranties of any kind are made as to their accuracy or suitability for particular applications. The data provided herein are based on laboratory work with small-scale test equipment, running at standard conditions, and do not necessarily match product performance in industrial use. New knowledge and experiences can lead to modifications and changes within a short time without prior notice.

BECAUSE CONDITIONS OF USE ARE OUTSIDE OF HABASIT'S AND ITS AFFILIATED COMPANIES CONTROL, WE CANNOT ASSUME ANY LIABILITY CONCERNING THE SUITABILITY AND PROCESS ABILITY OF THE PRODUCTS MENTIONED HEREIN. THIS ALSO APPLIES TO PROCESS RESULTS / OUTPUT / MANUFACTURING GOODS AS WELL AS TO POSSIBLE DEFECTS, DAMAGES, CONSEQUENTIAL DAMAGES, AND FURTHER-REACHING CONSEQUENCES.